

YOUR REF: -  
DATE RECEIVED: APR 12, 2013  
DATE REPORTED: APR 19, 2013

Report No. : **LPMI/11690/13**  
Company : **Messrs. SGS (Malaysia) Sdn. Bhd.**  
**Wisma SGS, Lot 603, Pandamaran,**  
**42000 Port Klang, Selangor D.E.**

### ANALYSIS REPORT

One (1) sample said to be **WOOD PELLET**, contained in a polythene bag, was received from M/s. SGS (Malaysia) Sdn. Bhd., Port Klang.

#### **SAMPLE DESCRIPTION :-**

CLIENT : **MESSRS. MYBIG SDN. BHD.**

On analysis of the sample, the following results were obtained:-

<u>TEST PARAMETERS</u>		<u>TEST METHODS</u>	<u>RESULTS</u>
Total Moisture, (ARB)	%	NTA 8200 BPM 4-02	7.5 (Seven decimal five)
Ash, (DB)	%	NTA 8200 BPM 4-01	1.5 (One decimal five)
Total Sulphur, (DB)	%	GRAVIMETRIC	0.05 (Zero decimal zero-five)
Gross Calorific Value, (DB)	kcal/kg	NTA 8200 BPM 4-05	4649 (Four six four nine)
Nitrogen, N, (DB)	%	KJEDAHL	0.49 (Zero decimal four-nine)

Note: = 1) DB (Dried Basis)  
2) ARB (As Received Basis)

#### Remark:

1. These test results are representative only of the sample received and are not intended to be representative of any lot, cargo or shipment.
2. This test report is not for L/C negotiation purposes.
3. **WARNING:** The sample(s) to which the findings recorded herein (the "Findings") relate was(were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativeness of any goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted.

SGS LABORATORY SERVICES (M) SDN. BHD.



YAZZMAN ALIFF YAHAYA  
B.Sc. (HONS) AMIC  
CHEMIST